

PRODUCT INFORMATION

WARADUR® LS

Product Description

WARADUR® LS consists of straight-chained monocarboxylic acids with a chain length in the range of mainly C28 – C32. INCI: Montan Acid Wax.

General Advantages

Thanks to its high acid number, WARADUR® LS can easily be saponified and is therefore ideal for the production of stable wax emulsions of many different kinds.

Examples of Use

- Technical emulsions
- Mould release formulations
- Wood protection
- Polishes

Delivery Specifications *

Characteristics	Unit	Target value	Method
Acid value *	mg KOH/g	120 – 130	ISO 2114
Drop point *	°C	82 – 88	ASTM 3954
Saponification value	mg KOH/g	approx. 145 – 165	ISO 3681
Colour	–	pale yellow	AA 3.2.1.505
Viscosity @ 120 °C	mPas	10 – 15	AA 3.2.1.520
Density	g/cm³	1.00 – 1.02	Ph. Eur. 2.2.5

Packaging and Handling

Physical form	Flakes, also available as powder
Packaging	Paper bag or Big Bag
Storage	Store at ambient temperature on a dry place. Protect from heat/overheating and direct sunlight. The maximum shelf life is 5 years after production. Thereafter, tests of the chemical characteristics are recommended. After delivery, a minimum remaining shelf life at the customer of 1.5 years is warranted.

Safety

WARADUR® LS

- is made from a fossil biological source
- is not classified as carcinogenic, mutagenic or reprotoxic; no health or environmental hazards are known, provided it is applied in industrial and professional settings

For more information, consult SDS.

Delivery Time and Availability

Standard delivery time: 2 – 3 weeks. Preconditions can be met for achieving shorter delivery times on standard products when demanded by the market.

Legislation

Food contact legislation:

- FDA 175.105 Adhesives
- FDA 177.2600 Rubber articles intended for repeated use
- FDA 176.210 Defoaming agents used in the manufacture of paper and paperboard
- Commission Regulation (EU) No 10/2011 of 14 January 2011 on plastic materials and articles intended to come into contact with food

Other legislation:

- REACh compliant
- RoHS and CONEG compliant

For further information, please contact application@voelpker.com.