

PRODUCT INFORMATION

WARADUR® OP

Product Description

WARADUR® OP is an ester wax consisting of esters of montanic acids with multihydroxyl alcohols. Montanic acids are straight-chained monocarboxylic acids with a chain length in the range of C28 – C32. The corresponding esters exhibit chain length in the range of C58 – C66 and provide this wax with a low volatility, good thermostability and low migration rates. WARADUR® OP contains calcium montanate in addition to the montanic acid esters.

General Advantages

Improves the wetting and dispersing in powder coatings. Excellent paste-forming properties. Improves scratch resistance and slip properties. In water based lacquers and wood stains emulsions of montan waxes contribute to abrasion resistance and mar/scuff resistance. Effective dispersing agent, good thermal stability, low volatility, non-migrating.

The above-mentioned properties arise in particular when the wax is processed into micronisate (10 µm).

Examples of Use

Acts as a rheology modifier in printing inks/print pastes due to superior paste-forming properties:

- dispersion aid in pigment concentrates
- micronisate used for the manufacture of "soft-feel" teletronic coatings
- used as scratch resistance improver
- matting agent in liquid lacquers

Delivery Specifications *

Characteristics	Unit	Target value	Method
Acid value *	mg KOH/g	7 – 14	ISO 2114
Drop point *	°C	99 – 105	ASTM 3954
Saponification value	mg KOH/g	approx. 110 – 130	ISO 3681
Colour	–	light yellowish	AA 3.2.1.505
Viscosity @ 120 °C	mPas	150 – 300	AA 3.2.1.520
Density	g/cm³	1.00 – 1.02	Ph. Eur. 2.2.5

Packaging and Handling

Physical form	Flakes or powder
Packaging	Paper bag or Big Bag
Storage	Store at ambient temperature on a dry place. Protect from heat/overheating and direct sunlight. The maximum shelf life is 5 years after production. Thereafter, tests of the chemical characteristics are recommended. After delivery, a minimum remaining shelf life at the customer of 1.5 years is warranted.

Safety

WARADUR® OP

- is made from a fossil biological source
- in a test for ready biodegradability WARADUR® OP showed 22 % biodegradability, which can be considered as indication for inherent primary biodegradability, according to OECD (2006)
- is not classified as carcinogenic, mutagenic or reprotoxic; no health or environmental hazards are known, provided it is applied in industrial and professional settings

Delivery Time and Availability

Standard delivery time: 2 – 3 weeks. Preconditions can be met for achieving shorter delivery times on standard products when demanded by the market.

Legislation

Food contact legislation:

- FDA 175.105 Adhesives
- FDA 177.2600 Rubber articles intended for repeated use
- FDA 178.3770 For use in lubricants in the fabrication of vinyl chloride plastic food contact articles
- Commission Regulation (EU) No 10/2011 of 14 January 2011 on plastic materials and articles intended to come into contact with food

Other legislation:

- REACH, RoHS and CONEG compliant
- Listed in all relevant national inventories

For further information, please contact application@voelpker.com.

The information contained herein is believed to be accurate and reliable as of the date issued. However, we do not warrant or guarantee the accuracy or reliability, in particular not for any specific intended use by the customer. It is the responsibility of those to whom we supply our products directly or indirectly to ensure that their use of the products complies with existing regulations, laws, legislations and proprietary rights. The information given by Voelpker Spezialprodukte does not exempt the customer from carrying out inspections and analyses on goods purchased.

Issued: 2021-08-02, supersedes all previous editions

Voelpker Spezialprodukte GmbH · Fabrikstraße 1 · 39393 Völpke · Germany · Telephone +49 39402 962-0 · www.voelpker.com

