

PRODUCT INFORMATION

WARADUR® GSM

Product Description

WARADUR® GSM is an ester wax consisting of an ester mixture of long-chain aliphatic acids.

General Advantages

High effectiveness at low concentrations (0.3 – 0.8 phr), release agent, flow improver.

Examples of Use

Lubricant for rigid PVC processing, especially films and profiles. Flow improvement, mould release of TPU.

Delivery Specifications *

Characteristics	Unit	Target value	Method
Acid value *	mg KOH/g	10 – 15	ISO 2114
Drop point *	°C	75 – 80	ASTM 3954
Saponification value	mg KOH/g	approx. 155 – 180	ISO 3681
Colour	–	pale yellow	AA 3.2.1.505
Viscosity @ 120 °C	mPas	approx. 10 – 20	AA 3.2.1.520
Density	g/cm ³	approx. 1.00 – 1.02	Ph. Eur. 2.2.5

Packaging and Handling

Physical form	Flakes or powder
Packaging	Paper bag or Big Bag
Storage	Store at ambient temperature on a dry place. Protect from heat/overheating and direct sunlight. The maximum shelf life is 5 years after production. Thereafter, tests of the chemical characteristics are recommended. After delivery, a minimum remaining shelf life at the customer of 1.5 years is warranted.

Safety

WARADUR® GSM

- is made from regrowing and fossil biological sources
- is not classified as carcinogenic, mutagenic or reprotoxic; no health or environmental hazards are known, provided it is applied in industrial and professional settings

Delivery Time and Availability

Standard delivery time: 2 – 3 weeks. Preconditions can be met for achieving shorter delivery times on standard products when demanded by the market.

Legislation

Food contact legislation:

- Product for technical applications; not food contact compliant.

Other legislation:

- REACH, RoHS and CONEG compliant
- Components listed in all relevant national inventories

For further information, please contact application@voelpker.com.